

# Wear-resistant Steel Mechanical Properties

Grade	Tensile Strength	Elongation	Impact test (-20°)	HBW
NM360	>1100	>12	>24	330-390
NM400	>1200	>10	>24	370-430
NM450	>1250	>7	>24	420-480
NM500	/	/	/	>470
NM550	/	/	/	>530
NM600	1	/	/	>570