

Wear-resistant Steel Chemical Composition

Grade	C	Si	Mn	P	S	Cr	Mo	Ni	Bt
NM360	<0.25	<0.70	<1.60	<0.025	<0.015	<0.80	<0.50	<0.50	0.0005-0.006
NM400	<0.30	<0.70	<1.60	<0.025	<0.010	<1.00	<0.50	<0.70	0.0005-0.006
NM450	<0.35	<0.70	<1.70	<0.025	<0.010	<1.10	<0.55	<0.80	0.0005-0.006
NM500	<0.38	<0.70	<1.70	<0.020	<0.010	<1.20	<0.65	<1.00	0.0005-0.006
NM550	<0.38	<0.70	<1.70	<0.020	<0.010	<1.20	<0.70	<1.00	0.0005-0.006
NM600	<0.45	<0.70	<1.90	<0.020	<0.010	<1.50	<0.80	<1.00	0.0005-0.006